

Appendix 7

Sound absorption coefficient according to SS-EN ISO 11654																																									
Measurement of sound absorption coefficient in a reverberation room																																									
Client:	Saint-Gobain Ecophon AB	Date of test:	2024-06-13																																						
Description:	ODS 200 mm																																								
Object:	Fade ONE Smooth 15 mm																																								
Empty reverberation room:		Reverberation room with object																																							
Relative humidity:	79,3 %	Relative humidity:	80,8 %																																						
Temperature:	21,8 °C	Temperature:	22,0 °C																																						
Barometric pressure:	98,9 kPa	Barometric pressure:	99,0 kPa																																						
Surface area:	10,80 m ²																																								
Room volume:	200,0 m ³																																								
Total room area S _t :	211,4 m ²																																								
<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th style="padding: 5px;">Frequency f [Hz]</th> <th style="padding: 5px;">α_p 1/1octave</th> </tr> </thead> <tbody> <tr><td style="padding: 5px;">100</td><td style="padding: 5px;"></td></tr> <tr><td style="padding: 5px;">125</td><td style="padding: 5px;">0,35</td></tr> <tr><td style="padding: 5px;">160</td><td style="padding: 5px;"></td></tr> <tr><td style="padding: 5px;">200</td><td style="padding: 5px;"></td></tr> <tr><td style="padding: 5px;">250</td><td style="padding: 5px;">0,70</td></tr> <tr><td style="padding: 5px;">315</td><td style="padding: 5px;"></td></tr> <tr><td style="padding: 5px;">400</td><td style="padding: 5px;"></td></tr> <tr><td style="padding: 5px;">500</td><td style="padding: 5px;">0,75</td></tr> <tr><td style="padding: 5px;">630</td><td style="padding: 5px;"></td></tr> <tr><td style="padding: 5px;">800</td><td style="padding: 5px;"></td></tr> <tr><td style="padding: 5px;">1000</td><td style="padding: 5px;">0,70</td></tr> <tr><td style="padding: 5px;">1250</td><td style="padding: 5px;"></td></tr> <tr><td style="padding: 5px;">1600</td><td style="padding: 5px;"></td></tr> <tr><td style="padding: 5px;">2000</td><td style="padding: 5px;">0,90</td></tr> <tr><td style="padding: 5px;">2500</td><td style="padding: 5px;"></td></tr> <tr><td style="padding: 5px;">3150</td><td style="padding: 5px;"></td></tr> <tr><td style="padding: 5px;">4000</td><td style="padding: 5px;">0,90</td></tr> <tr><td style="padding: 5px;">5000</td><td style="padding: 5px;"></td></tr> </tbody> </table>	Frequency f [Hz]	α _p 1/1octave	100		125	0,35	160		200		250	0,70	315		400		500	0,75	630		800		1000	0,70	1250		1600		2000	0,90	2500		3150		4000	0,90	5000				
Frequency f [Hz]	α _p 1/1octave																																								
100																																									
125	0,35																																								
160																																									
200																																									
250	0,70																																								
315																																									
400																																									
500	0,75																																								
630																																									
800																																									
1000	0,70																																								
1250																																									
1600																																									
2000	0,90																																								
2500																																									
3150																																									
4000	0,90																																								
5000																																									
<table border="1" style="width: 100%; border-collapse: collapse;"> <tr> <td style="padding: 5px;">Weighted sound absorption coefficient according to ISO 11654</td> </tr> <tr> <td style="padding: 5px;">α_w = 0,75 (H) Classification: C</td> </tr> </table>				Weighted sound absorption coefficient according to ISO 11654	α _w = 0,75 (H) Classification: C																																				
Weighted sound absorption coefficient according to ISO 11654																																									
α _w = 0,75 (H) Classification: C																																									