

### Appendix 1

<b>Sound absorption coefficient according to SS-EN ISO 11654</b>																																																							
Measurement of sound absorption coefficient in a reverberation room																																																							
Client:	Saint-Gobain Ecophon AB	Date of test:	2024-09-26																																																				
Description:	ODS 200 mm																																																						
Object:	Fade ONE Smooth 40 mm (A)																																																						
Empty reverberation room:		Reverberation room with object:																																																					
Relative humidity:	81,9 %	Relative humidity:	80,5 %																																																				
Temperature:	20,8 °C	Temperature:	21,0 °C																																																				
Barometric pressure:	99,1 kPa	Barometric pressure:	99,1 kPa																																																				
Surface area:	10,80 m <sup>2</sup>																																																						
Room volume:	200,0 m <sup>3</sup>																																																						
Total room area S <sub>r</sub> :	211,4 m <sup>2</sup>																																																						
<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th style="padding: 5px;">Frequency f [Hz]</th> <th style="padding: 5px;">α<sub>p</sub> 1/1 octave</th> </tr> </thead> <tbody> <tr><td style="padding: 5px;">100</td><td style="padding: 5px;"></td></tr> <tr><td style="padding: 5px;">125</td><td style="padding: 5px;">0,35</td></tr> <tr><td style="padding: 5px;">160</td><td style="padding: 5px;"></td></tr> <tr><td style="padding: 5px;">200</td><td style="padding: 5px;"></td></tr> <tr><td style="padding: 5px;">250</td><td style="padding: 5px;">0,70</td></tr> <tr><td style="padding: 5px;">315</td><td style="padding: 5px;"></td></tr> <tr><td style="padding: 5px;">400</td><td style="padding: 5px;"></td></tr> <tr><td style="padding: 5px;">500</td><td style="padding: 5px;">0,80</td></tr> <tr><td style="padding: 5px;">630</td><td style="padding: 5px;"></td></tr> <tr><td style="padding: 5px;">800</td><td style="padding: 5px;"></td></tr> <tr><td style="padding: 5px;">1000</td><td style="padding: 5px;">0,90</td></tr> <tr><td style="padding: 5px;">1250</td><td style="padding: 5px;"></td></tr> <tr><td style="padding: 5px;">1600</td><td style="padding: 5px;"></td></tr> <tr><td style="padding: 5px;">2000</td><td style="padding: 5px;">0,95</td></tr> <tr><td style="padding: 5px;">2500</td><td style="padding: 5px;"></td></tr> <tr><td style="padding: 5px;">3150</td><td style="padding: 5px;"></td></tr> <tr><td style="padding: 5px;">4000</td><td style="padding: 5px;">1,00</td></tr> <tr><td style="padding: 5px;">5000</td><td style="padding: 5px;"></td></tr> </tbody> </table>	Frequency f [Hz]	α <sub>p</sub> 1/1 octave	100		125	0,35	160		200		250	0,70	315		400		500	0,80	630		800		1000	0,90	1250		1600		2000	0,95	2500		3150		4000	1,00	5000		<table border="1" style="width: 100%; border-collapse: collapse; margin-top: 10px;"> <caption>Data points for the graph</caption> <thead> <tr> <th>Frequency f [Hz]</th> <th>Practical sound absorption coefficient α<sub>p</sub></th> </tr> </thead> <tbody> <tr><td>125</td><td>0,35</td></tr> <tr><td>250</td><td>0,70</td></tr> <tr><td>500</td><td>0,80</td></tr> <tr><td>1000</td><td>0,90</td></tr> <tr><td>2000</td><td>0,95</td></tr> <tr><td>4000</td><td>1,00</td></tr> </tbody> </table>			Frequency f [Hz]	Practical sound absorption coefficient α <sub>p</sub>	125	0,35	250	0,70	500	0,80	1000	0,90	2000	0,95	4000	1,00
Frequency f [Hz]	α <sub>p</sub> 1/1 octave																																																						
100																																																							
125	0,35																																																						
160																																																							
200																																																							
250	0,70																																																						
315																																																							
400																																																							
500	0,80																																																						
630																																																							
800																																																							
1000	0,90																																																						
1250																																																							
1600																																																							
2000	0,95																																																						
2500																																																							
3150																																																							
4000	1,00																																																						
5000																																																							
Frequency f [Hz]	Practical sound absorption coefficient α <sub>p</sub>																																																						
125	0,35																																																						
250	0,70																																																						
500	0,80																																																						
1000	0,90																																																						
2000	0,95																																																						
4000	1,00																																																						
<div style="border: 1px solid black; padding: 10px;"> <p style="margin: 0;">Weighted sound absorption coefficient according to SS-EN ISO 11654</p> <p style="margin: 0;">α<sub>w</sub> = 0,90 <span style="float: right;">Classification: A</span></p> </div>																																																							